



DOW™ LDPE 722

The Dow Chemical Company - Low Density Polyethylene Resin

Thursday, December 21, 2023

General Information

Product Description

Dow™ LDPE 722 is used in flexible packaging and paperboard coating applications such as liquid/juice, laminate tube, condiment pouches, dry foods packaging, snack foods packaging, moist foods packaging, sugar pouches, lidding stock and medical packaging. DOW LDPE extrusion coating resins provide optimal neck-in and draw-down performance with minimal taste/odor contribution.

DOW Polyethylene 722 is a broad molecular weight distribution homopolymer designed to offer good impact strength and crack resistance, with excellent flexibility. The resin has good processability over a wide range of molding conditions.

- Typical applications include caps/closures
- Good impact, ESCR with excellent flexibility

Complies with:

- CANADIAN HPFB NO OBJECTION (WITH LIMITATIONS)
- EU, No 10/2011
- U.S. FDA 21 CFR 177.1520 (c) 2.2
- U.S. FDA DMF

Consult the regulations for complete details.

General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Latin America	• North America
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• DMF • EU No 10/2011	• FDA 21 CFR 177.1520(c) 2.2 • HPFB (Canada) No Objection ¹	
Forms	• Pellets		
Processing Method	• Extrusion Coating	• Injection Molding	

ASTM & ISO Properties²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.920	0.920	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) ³			ASTM D1693
122°F (50°C), 100% Igepal, F50	< 1.00 hr	< 1.00 hr	

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

DOW™ LDPE 722

The Dow Chemical Company - Low Density Polyethylene Resin

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ³			ASTM D638
Yield	1200 psi	8.27 MPa	
Break	1400 psi	9.65 MPa	
Tensile Elongation ³			ASTM D638
Yield	4.0 %	4.0 %	
Break	500 %	500 %	
Flexural Modulus - 2% Secant ³	34000 psi	234 MPa	ASTM D790B
Coefficient of Friction	0.60	0.60	ASTM D1894
Films	Typical Value (English)	Typical Value (SI)	Test Method
Seal Initiation Temperature ⁴	221 °F	105 °C	Internal Method
Water Vapor Transmission Rate	1.7 g·mil/ 100in ² /atm/24 hr	0.67 g·mm/m ² /atm/24 hr	ASTM F1249
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Impact Strength ^{5,3}	130 ft·lb/in ²	273 kJ/m ²	ASTM D1822
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness ³ (Shore D)	43	43	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load ³			ASTM D648
66 psi (0.45 MPa), Unannealed	99.0 °F	37.2 °C	
Brittleness Temperature ³	-76.0 °F	-60.0 °C	ASTM D746
Vicat Softening Temperature	190 °F	87.8 °C	ASTM D1525
Melting Temperature (DSC)	224 °F	107 °C	Internal Method
Peak Crystallization Temperature (DSC)	204 °F	95.6 °C	Internal Method
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Melt Temperature - Recommended	600 to 630 °F	316 to 332 °C	Internal Method

Fabrication Conditions For Extrusion Coating Film:

- Screw Size: 3.5 in. (89 mm); 30:1 L/D
- Screw Type: Single Flight with Maddock Mixer
- Die Gap: 20 mil (0.508 mm)
- Melt Temperature: 625°F (329°C)
- Output: 250 lb/hr
- Screw Speed: 90 rpm

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)	Test Method
Maximum Line Speed	25.0 ft/sec	7.6 m/sec	Internal Method
Minimum Coating Thickness	0.30 mil	7.6 µm	Internal Method
Minimum Coating Weight	4.4 lb/ream	7.2 g/m ²	Internal Method
Neck-in (610°F (321°C), 1.0 mil (25.4 µm))	2.0 in	50.8 mm	Internal Method

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

DOW™ LDPE 722

The Dow Chemical Company - Low Density Polyethylene Resin

Notes

¹ With limitations

² Typical properties: these are not to be construed as specifications.

³ Molded and tested in accordance with ASTM D4976.

⁴ Temperature at which 1 lb/in (4.4 N/25.4 mm) heat seal strength is achieved.

Heat Seal Strengths, Topware HT Tester 0.5 S dwell, 40 psi bar pressure, pull speed 250 mm/sec.

⁵ Type S

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.