

Bayblend® T65 XF

Covestro - Polycarbonates - Polycarbonate + ABS

Thursday, December 21, 2023

General Information

Product Description

(PC+ABS)-Blend; Vicat/B 120 temperature = 120°C; improved flow compared with T65

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Flow		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FORD WSS-M4D684-B1 • FORD WSS-M4D924-B1 • GM GMW15581P-ABS+PC-T2	• GM GMW15581P-ABS+PC-T2 Color: 901510 Black • GM GMW15581P-ABS+PC-T5 • GM GMW15581P-ABS+PC-T5 Color: 901510 Black	• GM QK 000195 Type B Color: 901510 Black • GM QK 002412 Color: 901510 Black
ISO Shortname	• PC+ABS		

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C))	1.13 g/cm ³	1.13 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	18 cm ³ /10min	18 cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 2577
Across Flow : 500°F (260°C), 0.118 in (3.00 mm)	0.50 to 0.70 %	0.50 to 0.70 %	
Flow : 500°F (260°C), 0.118 in (3.00 mm)	0.50 to 0.70 %	0.50 to 0.70 %	
Water Absorption			ISO 62
Saturation, 73°F (23°C)	0.70 %	0.70 %	
Equilibrium, 73°F (23°C), 50% RH	0.20 %	0.20 %	

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

Bayblend® T65 XF

Covestro - Polycarbonates - Polycarbonate + ABS

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	341000 psi	2350 MPa	ISO 527-1/1
Tensile Stress			ISO 527-2/50
Yield, 73°F (23°C)	7830 psi	54.0 MPa	
Break, 73°F (23°C)	6820 psi	47.0 MPa	
Tensile Strain			ISO 527-2/50
Yield, 73°F (23°C)	4.4 %	4.4 %	
Break, 73°F (23°C)	> 50 %	> 50 %	
Flexural Modulus ³ (73°F (23°C))	341000 psi	2350 MPa	ISO 178
Flexural Stress ³			ISO 178
3.5% Strain, 73°F (23°C)	10600 psi	73.0 MPa	
73°F (23°C)	12200 psi	84.0 MPa	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	17 ft·lb/in ²	36 kJ/m ²	
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-22°F (-30°C)	17 ft·lb/in ²	35 kJ/m ²	
73°F (23°C)	23 ft·lb/in ²	48 kJ/m ²	
Unnotched Izod Impact Strength			ISO 180
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	252 °F	122 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	216 °F	102 °C	ISO 75-2/A
Vicat Softening Temperature			
--	248 °F	120 °C	ISO 306/B120
--	244 °F	118 °C	ISO 306/B50
CLTE			ISO 11359-2
Flow : 73 to 131°F (23 to 55°C)	4.4E-5 in/in/°F	8.0E-5 cm/cm/°C	
Transverse : 73 to 131°F (23 to 55°C)	4.7E-5 in/in/°F	8.5E-5 cm/cm/°C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms·cm	1.0E+16 ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
73°F (23°C), 0.0394 in (1.00 mm)	890 V/mil	35 kV/mm	
Relative Permittivity			IEC 60250
73°F (23°C), 100 Hz	3.10	3.10	
73°F (23°C), 1 MHz	3.00	3.00	
Dissipation Factor			IEC 60250
73°F (23°C), 100 Hz	3.0E-3	3.0E-3	
73°F (23°C), 1 MHz	8.5E-3	8.5E-3	
Comparative Tracking Index (Solution A)	250 V	250 V	IEC 60112

Copyright ©, 2023 , Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

Bayblend® T65 XF

Covestro - Polycarbonates - Polycarbonate + ABS

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.03 in (0.9 mm))	HB	HB	UL 94
Oxygen Index ⁴	24 %	24 %	ISO 4589-2
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Melt Viscosity ⁵ (500°F (260°C))	200 Pa·s	200 Pa·s	ISO 11443-A

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Dry Air Dryer	203 to 230 °F	95 to 110 °C
Drying Time - Dry Air Dryer	4.0 hr	4.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	428 to 446 °F	220 to 230 °C
Middle Temperature	437 to 455 °F	225 to 235 °C
Front Temperature	446 to 464 °F	230 to 240 °C
Nozzle Temperature	491 to 509 °F	255 to 265 °C
Processing (Melt) Temp	464 to 518 °F	240 to 270 °C
Mold Temperature	158 to 194 °F	70 to 90 °C
Back Pressure	725 to 2180 psi	5.00 to 15.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s
 Standard Melt Temperature: 260°C
 Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

¹ Typical properties: these are not to be construed as specifications.

² 150x105x3mm,, MT 80°C

³ 0.079 in/min (2.0 mm/min)

⁴ Procedure A

⁵ 1000s-1

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.