

Product Description

High-performance thermoplastic material, unreinforced PolyEtherEtherKetone (PEEK), semi-crystalline, granules for injection moulding and extrusion, standard flow, FDA food contact compliant, colour natural/beige.

Typical Application Areas

Applications for higher strength and stiffness as well as high ductility. Chemically resistant to aggressive environments, suitable for sterilisation for medical and food contact applications.

MATERIAL PROPERTIES				
	CONDITIONS	TEST METHOD	UNITS	TYPICAL VALUE
Mechanical Data				
Tensile Strength	Yield, 23°C	ISO 527	MPa	98
Tensile Elongation	Break, 23°C	ISO 527	%	45
Tensile Modulus	23°C	ISO 527	GPa	4.0
Flexural Strength	At 3.5% strain, 23°C	ISO 178	MPa	125
	At yield, 23°C			165
	125°C			85
	175°C			19
	275°C			12.5
Flexural Modulus	23°C	ISO 178	GPa	3.8
Compressive Strength	23°C	ISO 604	MPa	125
	120°C			70
Charpy Impact Strength	Notched, 23°C	ISO 179/1eA	kJ m ⁻²	7.0
	Unnotched, 23°C	ISO 179/1U		n/b
Izod Impact Strength	Notched, 23°C	ISO 180/A	kJ m ⁻²	8.0
	Unnotched, 23°C	ISO 180/U		n/b
Thermal Data				
Melting Point		ISO 11357	°C	343
Glass Transition (Tg)	Onset	ISO 11357	°C	143
	Midpoint			150
Coefficient of Thermal Expansion	Along flow below Tg	ISO 11359	ppm K ⁻¹	45
	Average below Tg			55
	Along flow above Tg			120
	Average above Tg			140
Heat Deflection Temperature	As moulded, 1.8 MPa	ISO 75-f	°C	152
Thermal Conductivity	Along flow, 23°C	ISO 22007-4	W m ⁻¹ K ⁻¹	0.32
	Average, 23°C			0.29
Relative Thermal Index	Electrical	UL 746B	°C	260
	Mechanical w/o impact			240
	Mechanical w/impact			180
Flow				
Melt Viscosity	400°C	ISO 11443	Pa.s	350
Miscellaneous				
Density	Crystalline	ISO 1183	g cm ⁻³	1.30
Shore D hardness	23°C	ISO 868		84.5
Water Absorption by immersion	Saturation, 23°C	ISO 62-1	%	0.45
	Saturation, 100°C			0.55

Electrical Properties					
Dielectric Strength	2mm thickness	IEC 60243-1	kV mm ⁻¹	23	
	50 µm thickness			200	
Comparative Tracking Index		IEC 60112	V	150	
Loss Tangent	23°C, 1 MHz	IEC 60250	n/a	0.004	
Dielectric Constant	23°C, 1 kHz	IEC 60250	n/a	3.1	
	23°C, 50 kHz			3.0	
	200°C, 50 kHz			4.5	
Volume Resistivity	23°C	IEC 60093	Ω cm	10 ¹⁶	
	125°C			10 ¹⁵	
	275°C			10 ⁹	
Fire Smoke Toxicity					
Glow Wire Test	2mm thickness	IEC 60695-2-12	°C	960	
Limiting Oxygen Index	0.4 mm thickness	ISO 4589	% O ₂	24	
	3.2 mm thickness			35	
Toxicity Index	CO content	NES 713	n/a	0.074	
	CO ₂ content			0.15	
	Total gases			0.22	
Typical Processing					
Drying Temperature / Time	150°C / 3h or 120°C / 5h (residual moisture <0.02%)				
Temperature settings	355 / 360 / 365 / 370 / 375°C (Nozzle)				
Hopper Temperature	Not greater than 100°C				
Mould Temperature	170°C - 200°C				
Runner	Die / nozzle >3mm, manifold >3.5mm				
Gate	>1 mm or 0.5 x part thickness				
Mould Shrinkage + spiral flow					
Spiral Flow	375°C nozzle, 190°C tool	1mm thick section	Victrex	mm	110
Mould Shrinkage	375°C nozzle, 190°C tool	Along flow	ISO 294-4	%	1.0
		Across flow			1.3

Important notes:

- Processing conditions quoted in our datasheets are typical of those used in our processing laboratories
 - Data for mould shrinkage should be used for material comparison. Actual mould shrinkage values are highly dependent on part geometry, mould configuration, and processing conditions.
 - Mould shrinkage differs for along flow and across flow directions. "Along flow" direction is taken as the direction the molten material is travelling when it exits the gate and enters the mould.
 - Mould shrinkage is expressed as a percent change in dimension of a specimen in relation to mould dimensions.
- Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison. Actual property values are highly dependent on part geometry, mould configuration and processing conditions. Properties may also differ for along flow and across flow directions.

Detailed data available on our website www.victrex.com or upon request.

World Headquarters

Victrex plc
 Hillhouse International
 Thornton Cleveleys, Lancashire
 FY5 4QD, United Kingdom
 TEL +44 (0)1253 897700
 FAX +44 (0)1253 897701
 MAIL victrexplc@victrex.com



Victrex plc and/or its group companies (**Victrex plc**) believes that the information contained in this document is an accurate description of the typical characteristics and/or uses of the product(s) and is based on information that we believe is reliable. However, it is provided for information only. It is not intended to amount to advice on which you should rely and should not be construed as, or used as a substitute for, professional or specialist advice. In particular, it is the customer's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy, and safety for each end-use product, device or other application. Suggestions of product uses should not be taken as inducements to infringe any particular patent. Mention of a product in this document is not a guarantee of its availability.

Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development. Victrex plc makes no warranties, express or implied, including, without limitation, a warranty of fitness for a particular purpose or of intellectual property non-infringement, including but not limited to patent non-infringement, which are expressly disclaimed, whether express or implied, in fact or by law.

Further, Victrex plc makes no warranty to your customers or agents and has not authorised anyone to make any representation or warranty other than as provided above.

Victrex plc shall in no event be liable for any general, indirect, special, consequential, punitive, incidental or similar damages, or any damages for harm to business, lost profits or lost savings, even if Victrex has been advised of the possibility of such damages regardless of the form of action. The foregoing does not seek to affect any liability (including to individual consumers) which cannot be excluded or limited under any applicable law.

Supporting information is available on request for claims referenced in this document.

Victrex plc is the owner or the licensee of all intellectual property rights in this document. All rights are protected by copyright and other intellectual property laws and treaties around the world. All rights reserved.

VICTREX™, APTIV™, VICOTE™, VICTREX PIPES™, VICTREX HT™, VICTREX ST™, VICTREX WG™, VICTREX FG™, VICTREX HPG™, VICTREX AE™, VICTREX CT™ and SHAPING FUTURE PERFORMANCE™ are trademarks of Victrex plc or its group companies.