

TECAFINE PE100 black - Stock Shapes

Chemical Designation

PE 100 (High Density Polyethylene)

Colour

white opaque

Density

0.96 g/cm³

Main features

- excellent chemical resistance
- heat stabilized
- good machinability
- high stiffness
- high toughness

Target Industries

- agricultural machinery
- automotive industry
- chemical technology
- pharmaceutical industry

| Mechanical properties | parameter | value | unit | norm | comment |
|---|------------------|--------------------|----------------------------------|----------------------|---|
| Modulus of elasticity (tensile test) | | 1100 | MPa | DIN EN ISO 527-1 | (1) n.b. = not broken |
| Tensile strength at yield | | 23 | MPa | DIN EN ISO 527-1 | |
| Elongation at yield | | 9 | % | DIN EN ISO 527-1 | |
| Impact strength (Charpy) | | n.b. | kJ/m ² | DIN EN ISO 179-1 | 1) |
| Shore hardness | Shore D | 64 | | DIN EN ISO 868 | |
| Ball indentation hardness | | 40 | MPa | - | |
| Thermal properties | parameter | value | unit | norm | comment |
| Service temperature | | -50 - +80 | °C | - | 1) |
| Thermal expansion (CTE) | | 18 | 10 ⁻⁵ K ⁻¹ | DIN EN ISO 11359-1;2 | (1) Found in public sources. Individual testing regarding application conditions is mandatory. |
| Electrical properties | parameter | value | unit | norm | comment |
| surface resistivity | | ≥ 10 ¹⁴ | Ω | DIN IEC 60093 | |
| Dielectric strength | | 47 | kV/mm | ISO 60243-1 | |
| Other properties | parameter | value | unit | norm | comment |
| Flammability | corresponding to | B2 | | DIN 4102 | 1) (1) Corresponding means no listing. The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory. |

Ensinger Ltd
Wilfried Way
Tonyrefail, Mid Glamorgan CF39 8JQ
Great Britain

Phone (01443) 678400
Fax (01443) 675777
ensingerplastics.com

Date: 2017/10/25

Version: AA